

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 308 494 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
07.05.2003 Bulletin 2003/19

(51) Int Cl.7: C09K 11/06, H05B 33/14,
H01L 51/20

(21) Application number: 02257505.4

(22) Date of filing: 29.10.2002

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR
Designated Extension States:
AL LT LV MK RO SI

- Miyaguchi, Satoshi,
c/o Corporate R&D Laboratory
Tsurugashima-shi, Saitama 350-2288 (JP)
- Wakimoto, Takeo,
c/o Corporate R&D Laboratory
Tsurugashima-shi, Saitama 350-2288 (JP)

(30) Priority: 31.10.2001 JP 2001334325

(71) Applicant: Pioneer Corporation
Meguro-ku, Tokyo (JP)

(74) Representative:
Luckhurst, Anthony Henry William
MARKS & CLERK,
57-60 Lincoln's Inn Fields
London WC2A 3LS (GB)


(72) Inventors:
• Tsuji, Tai-shi, c/o Corporate R&D Laboratory
Tsurugashima-shi, Saitama 350-228 (JP)

(54) Organic electroluminescence element

(57) An organic electroluminescence element has an anode, a hole transport layer, a light emitting layer made of organic compounds, an electron transport layer and a cathode. The light emitting layer comprises an organic host material having an electron transport capability and an organic guest material of phosphorescent

material. An ionization potential energy of the organic host material is higher than that of the hole transport layer. The difference in the ionization potential energy between the organic host material of the light emitting layer and the hole transport layer is in a range from 0.4 eV to 0.8 eV.

FIG. 1



Description

BACKGROUND OF THE INVENTION

1. Technical Field

[0001] The present invention relates to an organic electroluminescence element (hereinafter also referred to as the "organic EL element") which utilizes the electroluminescence (hereinafter also referred to as the "EL") of organic compounds which emit light in response to a current injected thereto, and has a light emitting layer formed of a laminate of such materials.

2. Description of the Related Art

[0002] Generally, each of the organic EL elements constituting a display panel using organic materials comprises an anode as a transparent electrode, a plurality of organic material layers including an organic light emitting layer, and a cathode comprised of a metal electrode, which are laminated as thin films in this order on a glass substrate as a display surface. The organic material layers include, in addition to the organic light emitting layer, a layer of a material having the hole transport capability such as a hole injection layer and a hole transport layer, a layer of a material having the electron transport capability such as an electron transport layer and an electron injection layer, and so on. Organic EL elements comprising these layers are also proposed. The electron injecting layer also contains an inorganic compound.

[0003] As an electric field is applied to the laminate organic EL element including an organic light emitting layer and an electron or hole transport layer, the holes are injected from the anode, while electrons are injected from the cathode. The electrons and the holes are recombined in the organic light emitting layer to form excitons. The organic EL element utilizes light which is emitted when the excitons return to a base state. In some cases, a pigment may be doped into the light emitting layer for improving the efficiency of light emission and stably driving the element.

[0004] Recently, it is suggested that phosphorescent materials are used for the light emitting layer of the organic EL element in addition to fluorescent materials.

[0005] It is expected that the ratio of production of singlet and triplet excited states is 1:3 because the EL element using phosphorescence may achieve an high light efficiency as three or four times of the device using fluorescence.

[0006] On the other hand, for improving the low power consumption nature, light emission efficiency, and driving stability of the organic EL element, it has been proposed to provide a hole blocking layer between the organic light emitting layer and the cathode for limiting the migration of holes from the organic light emitting layer. Efficient accumulation of holes in the light emitting layer with the aid of the hole blocking layer can result in an improved recombination probability with electrons, and a higher light emission efficiency. A report has been made that single use of a phenanthroline derivative or a triazole derivative is effective as a hole blocking material (see Japanese Patent Application Kokai Nos. Hei 8-109373 and Hei 10-233284).

[0007] There is an organic EL element utilizing emission of phosphorescence. The conventional organic EL element comprises a light emitting layer including a material having a hole transport capability as a host material; and a hole blocking layer disposed at the side of the cathode adjacent to the light emitting layer and having an ionization potential energy higher than that of the light emitting layer's host material, for example, a phenanthroline derivative such as 2,9-dimethyl-4,7-diphenyl-, 1,10-phenanthroline: BCP, or an aluminum chelate such as ((1,1'-biphenyl)-4-olato)bis(2-methyl-8-quinolinolato Ni, O8) aluminum: BAQ. When BCP is used for the hole blocking layer, there is a drawback in that the driving lifetime of the organic EL element is very short although the early emission property thereof is good. There is no material for the hole blocking layer having both of an excellent durability and a high ionization potential energy enough to block holes in the actual situation at the present time.

[0008] Although BAQ has an excellent durability but not a sufficient hole blocking capability because of a less than a high ionization potential energy. In fact, when an organic EL element utilizing the hole blocking layer of BAQ and the electron transport layer of tris(8-hydroxyquinolato Ni, O8) aluminum: Alq3 is driven, the electron transport layer emits green light. If such an organic EL element utilizes phosphorescence for red emission, the green light emitted from Alq3 influences chromatic deterioration itself so that red emission changes into orange.

[0009] While the provisions of an organic phosphorescent material light emitting layer and a hole blocking layer is effective for increasing the light emission efficiency of the organic EL element, a longer lifetime of the element is required. There is a need for a highly efficient organic electroluminescence element which continuously emits light at a high luminance with a less current.

OBJECT AND SUMMARY OF THE INVENTION

[0010] It is an object of the present invention to provide an organic EL element having effectiveness in prolonging life time.

[0011] An organic electroluminescence element according to the present invention comprises: an anode, a hole transport layer, a light emitting layer made of organic compounds, an electron transport layer and a cathode, characterized

in that said light emitting layer comprises an organic host material having an electron transport capability and an organic guest material of phosphorescent material;


in that an ionization potential energy of said organic host material is higher than that of said hole transport layer; and

in that the difference in the ionization potential energy between said organic host material of said light emitting layer and said hole transport layer is in a range from 0.4 eV to 0.8 eV.

[0012] In one aspect of the invention, the organic electroluminescence element further includes a hole injecting layer disposed between said anode and said hole transport layer.

[0013] In another aspect of the invention, the organic electroluminescence element further includes an electron injecting layer disposed between said cathode and said electron transport layer.

[0014] In a further aspect of the organic electroluminescence element of the invention, said hole transport layer comprises a triphenylamine derivative, said organic host material comprises an aluminium chelate complex represented by a general formula (A)




wherein R2 denotes an alkyl, oxy, amino or hydrocarbon substituent having at least 1 carbon atom, carbon atom being 1 to 10 in any one hydrocarbon moiety,

R3 to R7 independently denote a hydrogen atom, alkyl, oxy, amino or hydrocarbon substituent having at least 1 carbon atom, carbon atom being 1 to 10 in any one hydrocarbon moiety,

R5, R6 and R7 are selected from a group comprises of cyano, halogen, and α -haloalkyl, α -haloalkoxy, amido, sulfonyl, carbonyl, carbonyloxy and oxycarbonyl substituents containing up to 10 carbon atoms,

L denotes one of formulae (B) represented below



wherein R8 to R12 independently represent hydrogen or hydrocarbon groups of from 1 to 12 carbon atoms, with the proviso that R8 and R9 together or R9 and R10 together can form a fused benzo ring,

R13 to R27 independently represent hydrogen or hydrocarbon groups of from 1 to 12 carbon atoms, with the proviso that R13 and R14 or R14 and R15 can form a fused benzo ring, R18 and R19 or R19 and R20 can form a fused benzo ring, and R23 and R24 or R24 and R25.

[0015] In a still further aspect of the organic electroluminescence element of the invention, said hole transport layer comprises 4,4'-bis(N-(naphthyl)-N-phenylamino)biphenyl, said organic host material comprises ((1,1'-biphenyl)-4-olato) bis(2-methyl-8-quinolinolato Ni, 08) aluminum.

[0016] In a still further aspect of the organic electroluminescence element of the invention, said hole transport layer comprises 4,4'-bis(N-(naphthyl)-N-phenylamino)biphenyl, said organic host material comprises bis(2-methyl-8-hydroxyquinolinato) gallium chloride.

BRIEF DESCRIPTION OF THE DRAWINGS

[0017]

Figs. 1 to 3 are cross-sectional diagrams each schematically illustrating an organic EL element in embodiments according to the present invention; and

Figs. 4 and 5 are graphs each showing a luminance property vs. passage of driving time of the EL element of the embodiment according to the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0018] An embodiment of the present invention will hereinafter be described with reference to the accompanying drawings.

[0019] An organic EL element according to the present invention basically comprises an anode 2, a hole transport layer 3, a light emitting layer 4, an electron transport layer 6 and a cathode 7 as illustrated in Fig. 1. For example, a transparent anode 2; a hole transport layer 3 made of an organic compound; a light emitting layer 4 made of an organic compound; an electron transport layer 6 made of an organic compound; and a cathode 7 made of a metal having a low work function are laminated in this order on a transparent substrate 1 such as glass, so that an organic EL element is completed. The light emitting layer 4 of the organic EL element according to the embodiment of the present invention comprises of an organic host material made of at least one organic compound having an electron transport capability and a guest material made of at least one organic phosphorescent material doped into the host material. The organic host material of the light emitting layer 4 has an ionization potential energy (Ip) higher than that of the organic compound used for the hole transport layer 3 so that the difference in the ionization potential energy between the organic host

material of the light emitting layer 4 and the hole transport layer 3 is in a range from 0.4 eV to 0.8 eV. In the light emitting layer 4, one of the organic guest materials is preferably doped in a proportion ranging from 4 to 10 % in weight percentage to all materials contained therein.


[0020] In a concrete example of the organic EL element, the anode is made of ITO; the hole transport layer is made of 4,4'-bis(N-(naphthyl)-N-phenyl-amino)biphenyl: NPB (Ip = 5.4 eV); the host material of the light emitting layer is made of ((1,1'-biphenyl)-4-olato)bis(2-methyl-8-quinolinolato Ni, 08) aluminum: BAlq (Ip = 5.9 eV); and the electron transport layer is made of Alq3; and the cathode is made of aluminum.


[0021] In addition to the foregoing structure, another organic EL element may have a structure which includes an electron injecting layer 7a of Li₂O or the like laminated or deposited as a thin film between the electron transport layer 6 and the cathode 7, as illustrated in Fig. 2.

[0022] In addition to the structure of the organic EL element above mentioned, other embodiments include an organic EL element further comprising a hole injecting layer 3a disposed between the anode 2 and the hole transport layer 3 as shown in Fig. 3. The hole injecting layer 3a may be made of copper phthalocyanine (so-called CuPc) included in porphyrin derivatives having a hole transport capability.


[0023] As the cathode 7, there may be used a metal which has a small work function, for example, aluminum, magnesium, indium, silver, and alloys thereof, and a thickness in a range of approximately 100 to 5000 angstroms. Also, as the anode 2, there may be mentioned a conductive material which has a large work function, for example, indium tin oxide (hereinafter abbreviated as "ITO"), and a thickness in a range of approximately 300 to 3000 angstroms, or gold of approximately 800 to 1500 angstroms in thickness. It should be noted that when gold is used as an electrode material, the electrode is translucent. Either the cathode or the anode may be transparent or translucent.

[0024] In the embodiments, the substance contained in the hole transport layer 3 having the hole transport capability may be selected from materials represented by the following chemical formulae (1) - (26) including triphenylamine derivatives.






(2)









(3)




(4)


-17-









(11)




(12)




(13)






(14)







(15)




(16)









(23)



(24)









(25)









(26)


[0025] The organic host material having the electron transport capability which is a major component of the light emitting layer 4 is selected as a material whose ionization potential (Ip) is higher than that of the organic compound of the hole transport layer 3 by a difference ranging from 0.4 eV to 0.8 eV. Such an organic host material may be selected from materials represented by the following chemical formulae (27) - (45).






















[0026] In the above formulae, Bu represents a butyl group; and t-Bu represents a tert-butyl group.

[0027] In the embodiments, the organic host material contained in the light emitting layer 4 having the electron transport capability also may be selected from aluminium chelate complexes or coordination complexes represented by a general formula (A)




20 wherein R2 denotes an alkyl, oxy, amino or hydrocarbon substituent having at least 1 carbon atom, carbon atom being 1 to 10 in any one hydrocarbon moiety,

R3 to R7 independently denote a hydrogen atom, alkyl, oxy, amino or hydrocarbon substituent having at least 1 carbon atom, carbon atom being 1 to 10 in any one hydrocarbon moiety,

25 R5, R6 and R7 are selected from a group comprises of cyano, halogen, and α -haloalkyl, α -haloalkoxy, amido, sulfonyl, carbonyl, carbonyloxy and oxycarbonyl substituents containing up to 10 carbon atoms,

L denotes one of formulae (B)






55 wherein R8 to R12 independently represent hydrogen or hydrocarbon groups of from 1 to 12 carbon atoms, with the proviso that R8 and R9 together or R9 and R10 together can form a fused benzo ring,

R13 to R27 independently represent hydrogen or hydrocarbon groups of from 1 to 12 carbon atoms, with the proviso that R13 and R14 or R14 and R15 can form a fused benzo ring, R18 and R19 or R19 and R20 can form a fused benzo ring, and R23 and R24 or R24 and R25.


[0028] In the aluminum chelates whose ionization potential (Ip) is higher than that of the organic compound of the

hole transport layer 3 by a difference ranging from 0.4 eV to 0.8 eV, the organic host material may be selected from materials represented by the following chemical formulae (46) - (81).








(48)




(49)







(52)




(53)




(54)




(55)




(56)




(57)




(58)



(59)



(60)





(61)




25




45











(66)




(67)















(74)




(75)















(80)




(81)

[0029] In further embodiments, the organic host material contained in the light emitting layer 4 having the electron transport capability also may be selected from materials represented by the following chemical formulae (82) - (90) or phenanthroline derivatives.







[0030] The organic guest material of phosphorescence included in the light emitting layer 4 is, for example, 2,3,7,8,12,13,17,18-octaethyl-21H,23H-porphine platinum (II), tris(2-phenylpyridine)iridium, bis(2-(2'-benzo[4,5- α]thienyl)pyridinato-N, C3)iridium and the like.

[0031] In the embodiments, the substance used for the electron transport layer 6 may be selected from the foregoing organic compound materials represented for the organic host material having the electron transport capability.

<EXPERIMENT 1>

[0032] Samples of several organic EL elements were specifically made for evaluating the characteristics thereof.

[0033] The respective samples were manufactured in such a manner that NPB is used for each hole transport layer, and Alq3 is used for each electron transport layer, and in that various host materials were used for the respective light emitting layers. The respective thin films of Samples or embodiments were laminated on a glass substrate formed with an anode made of ITO having a thickness of 1100 Å by a vacuum deposition method at the degree of vacuum of 5.0×10^{-6} Torr.

[0034] First, for Sample 1, NPB was formed in a thickness of 800 Å on the ITO anode as a hole transport layer at the deposition rate of 3 Å/sec.

[0035] Next, a host material of Alq3 and a guest material of red phosphorescent substance (hereinafter referred to as the "Dopant A") were co-evaporated from different evaporation sources in a thickness of 475 Å on the hole transport layer as a light emitting layer. In this event, the concentration of Dopant A in the light emitting layer was 7 wt. %.

[0036] Subsequently, on the light emitting layer, Alq3 was deposited as an electron transport layer in a thickness of 300 Å at the deposition rate of 3 Å/sec.

[0037] Further, on the electron transport layer, lithium oxide (Li_2O) was deposited as an electron injecting layer in a thickness of 5 Å at the deposition rate of 0.1 Å/sec, and then aluminum (Al) was laminated on the electron injecting layer as an electrode in a thickness of 1000 Å at the rate of 10 Å/sec to complete an organic light emitting element of Sample 1.

[0038] Another organic EL element of Sample 1 was also manufactured in a similar manner to Sample 1 except that the light emitting layer and the electron transport layer were formed in thicknesses of 625 Å and 150 Å respectively.

[0039] Furthermore, Samples 2 - 5 were also manufactured in a similar manner to Sample 1 except that various host materials were used for the emitting layers. The following Table 1 shows the host materials of the emitting layers, the layered structure (LS) of thickness, chromaticity coordinates (CHRO), luminance (LU), quantum yield (QY) and driving voltage (DV) corresponding to Samples 1 - 5 together with ionization potential energy (Ip).

Table 1

	HOST (Ip)	LS (Å)			CHRO		LU cd/m ²	QY %	DV V
		NPB/	HOST + A	/Alq3	CIE _x	CIE _y			
1	Alq3 (5.7 eV)	800/	475	/300	0.68	0.31	45	2.4	4.3
		800/	625	/150	0.68	0.32	44	2.3	4.4
2	BAIq (5.9 eV)	800/	475	/300	0.68	0.32	171	8.2	6.4
		800/	625	/150	0.68	0.32	182	8.7	7.1
3	Ga _q Me ₂ Cl (6.1 eV)	800/	475	/300	0.68	0.32	168	8.2	6.3
		800/	625	/150	0.68	0.32	171	8.5	7.1
4	BCP (6.4 eV)	800/	475	/300	0.68	0.32	140	6.6	5.2
		800/	625	/150	0.68	0.32	139	6.6	5.5
5	OXD-7 (6.5 eV)	800/	475	/300	0.68	0.32	67	3.1	4.1
		800/	625	/150	0.68	0.32	66	3.1	4.2

[0040] The light emitting layer of Sample 1 contains the host material of Alq3 (Ip = 5.7 eV). In this Sample, since the difference in the ionization potential energy between NPB and Alq3 is smaller than 0.4 eV, so that holes easily pass through the light emitting layer to reduce the generation efficiency for excitons. Therefore, the emission efficiency of this sample is insufficient.

[0041] With respect to Samples 2 and 3, the light emitting layer of Sample 2 contains the host material of BAIq (Ip = 5.9 eV). The light emitting layer of Sample 3 contains the host material of (2-methyl-8-hydroxyquinolino) gallium chloride: Ga_qMe₂Cl (Ip = 6.1 eV). Both the Samples have excellent emission efficiencies. In comparison with Samples having the light emitting layers with thicknesses of 475 Å and 625 Å in Samples 2 and 3 respectively, the 625 Å samples have high values in the luminance and the quantum yield. As seen from this fact, it is estimated that the emission region in the light emitting layer lies at least 475 Å or more in thickness.

[0042] The light emitting layer of Sample 4 contains the host material of BCP (Ip = 6.4 eV). The light emitting layer of Sample 5 contains the host material of 1,3-bis(2-(4-tert-butylphenyl)-1,3,4-oxadiazol-5-yl)benzene: OXD-7 (Ip = 6.5 eV). In both the Samples 4 and 5, since the difference in the ionization potential energy between NPB and the host material is larger than 0.8 eV, the emission efficiencies of these samples are insufficient. Therefore, it is assumed that such a large difference of ionization potential energy between NPB and the host material restricts the emission region adjacent to the interface of NPB in the light emitting layer. Since NPB serves as a deactivator for phosphorescence (triplet excitons), Samples 4 and 5 have low values in the luminance and the quantum yield in comparison with Samples 2 and 3.

[0043] Since NPB has ionization potential energy of 5.4 eV, Samples 2 and 3 correspond to the embodiment of the present invention, and Samples 1, 4 and 5 correspond to the Comparatives.

<EXPERIMENT 2>

[0044] For another embodiment, a NPB hole transport layer (600 Å thick), a light emitting layer having BAIq host material and Dopant A (300 Å thick), an Alq3 electron transport layer (650 Å thick), a Li₂O electron injecting layer (5 Å thick), and an Al electrode 1000 Å were in turn layered on the ITO anode formed on a substrate to complete an organic EL element. This embodiment is hereinafter abbreviated as "Host:BAIq element".

[0045] For Comparative 1, a NPB hole transport layer (600 Å thick), a light emitting layer having CBP host material and Dopant A (300 Å thick), a BCP hole blocking layer (100 Å thick), an Alq3 electron transport layer (650 Å thick), a Li₂O electron injecting layer (5 Å thick), and an Al electrode 1000 Å were in turn layered on the ITO anode formed on a substrate to complete an organic EL element. The Comparative 1 is hereinafter abbreviated as "HBL:BCP element". In addition, the CBP host material in the light emitting layer is 4,4'-N,N'-dicarbazol-biphenyl. Furthermore, Comparative 2 of an organic EL element was manufactured in a similar manner to Comparative 1 except that the BCP hole blocking layer (100 Å thick) was replaced with a BAIq hole blocking layer (100 Å thick). The Comparative 2 is hereinafter abbreviated as "HBL:BAIq element".

[0046] The following Table 2 shows luminance properties of the embodiment of Host:BAIq element, Comparative 1 of HBL:BCP element and Comparative 2 of HBL:BAIq element. In addition, Fig. 4 shows the driving lifetime characteristics of the foregoing elements under the condition of application of 2.5 mA/cm².

Table 2

	CHRO		LU cd/m ²	QY %	DV V
	CIE _x	CIE _y			
Host:BAIq	0.680	0.319	179.1	8.55	6.51
HBL:BCP	0.683	0.317	204.0	10.76	6.52
HBL:BAIq	0.662	0.328	202.0	9.60	6.21

[0047] As apparent from Table 2, the Host:BAIq element is inferior to Comparative by 10 % in the emission efficiency (quantum yield). However, as apparent from Fig. 4, the Host:BAIq element has the driving lifetime about 20 times as large as Comparative 1 of the HBL:BCP element having the BCP hole blocking layer. Also, the Host:BAIq element has the driving lifetime about 3 times as large as Comparative 2 of the HBL:BAIq element having the BAIq hole blocking layer.

<EXPERIMENT 3>

[0048] A further embodiment of an organic EL element was manufactured as a second Host:BAIq element in a similar manner to the Host:BAIq element except that red phosphorescent material of 2,3,7,8,12,13,17,18-octaethyl-21H,23H-porphine platinum (II) (hereinafter referred to as the "Dopant B") was used instead of Dopant A. Namely, the second Host:BAIq element was manufactured in a manner that a NPB hole transport layer (900 Å thick), a light emitting layer having BAIq host material and Dopant B (325 Å thick), an Alq3 electron transport layer (550 Å thick), a Li₂O electron injecting layer (5 Å thick), and an Al electrode 1000 Å were in turn layered on the ITO anode formed on a substrate.

[0049] Furthermore, a still further embodiment of an organic EL element was also manufactured in a similar manner to the second Host:BAIq element except that a host material is GaqMe2Cl used in Sample 3 of EXPERIMENT 1 and a guest material is Dopant B. This embodiment is hereinafter abbreviated as "Host:GaqMe2Cl element". Namely, the Host:GaqMe2Cl element was manufactured in a manner that a NPB hole transport layer (900 Å thick), a light emitting layer having GaqMe2Cl host material and Dopant B (325 Å thick), an Alq3 electron transport layer (550 Å thick), a Li₂O electron injecting layer (5 Å thick), and an Al electrode 1000 Å were in turn layered on the ITO anode formed on a substrate.

[0050] In addition, Comparative 3 of an organic EL element was manufactured in such a manner that the hole blocking layer provided between the light emitting layer and the electron transport layer. Namely, the Comparative 3 was manufactured in a manner that a NPB hole transport layer (600 Å thick), a light emitting layer having CBP host material and (300 Å thick), a BCP hole blocking layer (100 Å thick), an Alq3 electron transport layer (650 Å thick), a Li₂O electron injecting layer (5 Å thick), and an Al electrode 1000 Å were in turn layered on the ITO anode formed on a substrate. This Comparative 3 is hereinafter abbreviated as "HBL:BCP element". Furthermore, Comparative 4 of an organic EL element was manufactured in a similar manner to Comparative 3 except that the BCP hole blocking layer was replaced with a BAIq hole blocking layer. The Comparative 4 is hereinafter abbreviated as "HBL:BAIq element".

[0051] The following Table 3 shows luminance properties of the embodiments of Host:BAIq element and Host:GaqMe2Cl element and Comparative 3 of HBL:BCP element and Comparative 4 of HBL:BAIq element.

Table 3

	CHRO		LU cd/m ²	QY %	DV V
	CIE _x	CIE _y			
Host:BAIq	0.684	0.301	50.1	5.97	7.05
Host:GaqMe2Cl	0.701	0.288	42.9	5.49	7.68
HBL:BCP	0.72	0.28	71.5	8.46	8.29
HBL:BAIq	0.608	0.359	95.8	7.02	8.12

[0052] As apparent from Table 2, the embodiments of the Host:BAIq element and Host:GaqMe2Cl element had levels of efficiency (quantum yield) reduced by 30 % in comparison to Comparatives. However, the embodiments of organic EL elements maintained the level of red emission in NTSC standard coordinates as contrast with Comparatives emitting orange light. Comparative 4 of HBL:BAIq element having the BAIq hole blocking layer has a chromaticity of CIE_x = 0.608 and CIE_y = 0.359.

[0053] In addition, Fig. 5 shows the driving lifetime characteristics of the embodiment of Host:BAIq element under

the condition of application of 7.5 mA/cm², and also, Comparatives 3 and 4 under the condition of application of 5.0 mA/cm². As apparent from Fig. 5, the embodiment of Host:BAIq element comprising the light emitting layer having the BAIq host material has an excellent driving lifetime keeping the 97% initial luminance for 1700 hours.

[0054] According to the present invention of the organic EL element utilizing phosphorescence, since the organic host material of the light emitting layer thereof has an ionization potential energy higher than that of the organic compound used for the hole transport layer so that the difference in the ionization potential energy between the organic host material of the light emitting layer and the hole transport layer is in a range from 0.4 eV to 0.8 eV, the organic EL element has a long driving lifetime keeping the luminance characteristics.

[0055] According to the present invention, one of evaporation depositing step for the organic layers of the organic EL element may be omitted or the evaporation of the hole blocking layer is unnecessary, although it is necessary and indispensable for the conventional organic EL element the hole blocking layer.

[0056] It is understood that the foregoing description and accompanying drawings set forth the preferred embodiments of the invention at the present time. Various modifications, additions and alternative designs will, of course, become apparent to those skilled in the art in light of the foregoing teachings without departing from the spirit and scope of the disclosed invention. Thus, it should be appreciated that the invention is not limited to the disclosed embodiments but may be practiced within the full scope of the appended claims.

Claims

1. An organic electroluminescence element comprising:

an anode; a hole transport layer; a light emitting layer made of organic compounds; an electron transport layer; and a cathode,


wherein said light emitting layer comprises an organic host material having an electron transport capability and an organic guest material of phosphorescent material;

wherein an ionization potential energy of said organic host material is higher than that of said hole transport layer; and

wherein the difference in the ionization potential energy between said organic host material of said light emitting layer and said hole transport layer is in a range from 0.4 eV to 0.8 eV.

2. An organic electroluminescence element according to claim 1, further comprising a hole injecting layer disposed between said anode and said hole transport layer.

3. An organic electroluminescence element according to claim 1 or 2, wherein said hole transport layer comprises a triphenylamine derivative, said organic host material comprises an aluminum chelate complex represented by a general formula (A)




wherein R2 denotes an alkyl, oxy, amino or hydrocarbon substituent having at least 1 carbon atom, carbon atom being 1 to 10 in any one hydrocarbon moiety,

R3 to R7 independently denote a hydrogen atom, alkyl, oxy, amino or hydrocarbon substituent having at least 1 carbon atom, carbon atom being 1 to 10 in any one hydrocarbon moiety,

R5, R6 and R7 are selected from a group comprises of cyano, halogen, and α -haloalkyl, α -haloalkoxy, amido, sulfonyl, carbonyl, carbonyloxy and oxycarbonyl substituents containing up to 10 carbon atoms,

L denotes one of formulae (B)



wherein R8 to R12 independently represent hydrogen or hydrocarbon groups of from 1 to 12 carbon atoms, with the proviso that R8 and R9 together or R9 and R10 together can form a fused benzo ring,

R13 to R27 independently represent hydrogen or hydrocarbon groups of from 1 to 12 carbon atoms, with the proviso that R13 and R14 or R14 and R15 can form a fused benzo ring, R18 and R19 or R19 and R20 can form a fused benzo ring, and R23 and R24 or R24 and R25.

4. An organic electroluminescence element according to any one of preceding claims 1-3, further comprising an electron injecting layer disposed between said cathode and said electron transport layer.
5. An organic electroluminescence element according to any one of preceding claims 1, 2 and 4, wherein said hole transport layer comprises 4,4'-bis(N-(naphthyl)-N-phenyl-amino)biphenyl, said organic host material comprises ((1,1'-biphenyl)-4-olato)bis(2-methyl-8-quinolinolato NI, 08) aluminum.
6. An organic electroluminescence element according to any one of preceding claims 1, 2 and 4, wherein said hole transport layer comprises 4,4'-bis(N-(naphthyl)-N-phenyl-amino)biphenyl, said organic host material comprises bis(2-methyl-8-hydroxyquinolinato) gallium chloride.

FIG. 1




FIG. 2




FIG. 3




FIG. 4





FIG. 5





Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 308 494 A3**

(12) **EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:
26.11.2003 Bulletin 2003/48

(51) Int Cl.7: **C09K 11/06**, H05B 33/14,
H01L 51/20, H01L 51/30

(43) Date of publication A2:
07.05.2003 Bulletin 2003/19

(21) Application number: **02257505.4**

(22) Date of filing: **29.10.2002**

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR
Designated Extension States:
AL LT LV MK RO SI

- Miyaguchi, Satoshi,
c/o Corporate R&D Laboratory
Tsurugashima-shi, Saitama 350-2288 (JP)
- Wakimoto, Takeo,
c/o Corporate R&D Laboratory
Tsurugashima-shi, Saitama 350-2288 (JP)

(30) Priority: **31.10.2001 JP 2001334325**

(71) Applicant: **Pioneer Corporation**
Meguro-ku, Tokyo (JP)

(74) Representative:
Luckhurst, Anthony Henry William
MARKS & CLERK,
57-60 Lincoln's Inn Fields
London WC2A 3LS (GB)


(72) Inventors:
• **Tsuji, Taishi, c/o Corporate R&D Laboratory**
Tsurugashima-shi, Saitama 350-228 (JP)

(54) **Organic electroluminescence element**

(57) An organic electroluminescence element has an anode, a hole transport layer, a light emitting layer made of organic compounds, an electron transport layer and a cathode. The light emitting layer comprises an organic host material having an electron transport capability and an organic guest material of phosphorescent

material. An ionization potential energy of the organic host material is higher than that of the hole transport layer. The difference in the ionization potential energy between the organic host material of the light emitting layer and the hole transport layer is in a range from 0.4 eV to 0.8 eV.

FIG. 1



EP 1 308 494 A3



European Patent
Office

PARTIAL EUROPEAN SEARCH REPORT

Application Number

which under Rule 45 of the European Patent Convention EP 02 25 7505 shall be considered, for the purposes of subsequent proceedings, as the European search report

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	US 6 303 238 B1 (FORREST STEPHEN R ET AL) 16 October 2001 (2001-10-16) * the entire document *	1-6	C09K11/06 H05B33/14 H01L51/20 H01L51/30
A	WO 00 70655 A (UNIV PRINCETON ;UNIV SOUTHERN CALIFORNIA (US)) 23 November 2000 (2000-11-23) * the entire document *	1-6	
A	WO 01 41512 A (UNIV PRINCETON ;UNIV SOUTHERN CALIFORNIA (US)) 7 June 2001 (2001-06-07) * the entire document *	1-6	
A	US 6 287 712 B1 (FORREST STEPHEN R ET AL) 11 September 2001 (2001-09-11) * the entire document *	1-6	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C09K H05B H01L
INCOMPLETE SEARCH			
<p>The Search Division considers that the present application, or one or more of its claims, does/do not comply with the EPC to such an extent that a meaningful search into the state of the art cannot be carried out, or can only be carried out partially, for these claims.</p> <p>Claims searched completely :</p> <p>Claims searched incompletely :</p> <p>Claims not searched :</p> <p>Reason for the limitation of the search:</p> <p>see sheet C</p>			
Place of search		Date of completion of the search	Examiner
MUNICH		7 October 2003	Nemes, C
CATEGORY OF CITED DOCUMENTS		<p>T : theory or principle underlying the invention</p> <p>E : earlier patent document, but published on, or after the filing date</p> <p>D : document cited in the application</p> <p>L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>	
<p>X : particularly relevant if taken alone</p> <p>Y : particularly relevant if combined with another document of the same category</p> <p>A : technological background</p> <p>O : non-written disclosure</p> <p>P : intermediate document</p>			

EPO FORM 1503 (03.02.04) (P4/C07)



European Patent
Office

INCOMPLETE SEARCH
SHEET C

Application Number
EP 02 25 7505

Claim(s) searched completely:
5,6

Claim(s) searched incompletely:
1-4

Reason for the limitation of the search:

Present claims 1-4 relate to an extremely large number of possible organic electroluminescent elements. Support within the meaning of Article 84 EPC and disclosure within the meaning of Article 83 EPC is to be found, however, for only a very small proportion of the elements claimed. In the present case, the claims so lack support, and the application so lacks disclosure, that a meaningful search over the whole of the claimed scope is impossible. Consequently, the search has been carried out for those parts of the claims which appear to be supported and disclosed, namely for claims 5 and 6.

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 25 7505

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

07-10-2003

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6303238	B1	16-10-2001	AU 1070799 A	03-05-1999
			EP 1044586 A2	18-10-2000
			JP 2001520450 T	30-10-2001
			TW 476227 B	11-02-2002
			WO 9920081 A2	22-04-1999
			US 2001053463 A1	20-12-2001

WO 0070655	A	23-11-2000	AU 5004700 A	05-12-2000
			BR 0010424 A	13-02-2002
			TW 500787 B	01-09-2002
			WO 0070655 A2	23-11-2000
			US 2003017361 A1	23-01-2003
			US 2002034656 A1	21-03-2002

WO 0141512	A	07-06-2001	AU 1807201 A	12-06-2001
			CN 1413426 T	23-04-2003
			EP 1252803 A1	30-10-2002
			JP 2003515897 T	07-05-2003
			WO 0141512 A1	07-06-2001
			US 2003017361 A1	23-01-2003
			US 2002034656 A1	21-03-2002

US 6287712	B1	11-09-2001	AU 3486199 A	01-11-1999
			WO 9953724 A1	21-10-1999
			US 6210814 B1	03-04-2001
			US 6312836 B1	06-11-2001

EPO FORM P4459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82